## Basecoats 1181 SERIES JET BLACK FACTORY PACK



**Archemya's 1181 Jet Black Factory Pack Basecoat** offers the purest Jet Black finish for your automotive refinishing needs. Prepare the surface, mix the basecoat and paint it black.

- FAST DRY TIME
- EXCELLENT DURABILITY
- PURE JET BLACK FINISH
- MEETS ALL VOC EXPECTATIONS

VOC Content:	3.5 VOC*
% Solids:	41-42%
Viscosity (reduced-#2 Zahn):	18-19 sec***
Cure Time (70° F):	~30 min. **
Recommended Coats:	2-3 Med. Coats
Flash Time:	5-10 Min**

**Directions for Use:** For best results, carefully follow the instructions on the can. For more information about this product please refer to our Technical Data Sheet at www.ccgproducts.com.

## 1. Preparation:


Prepare the surface with 480-600 grit dry sanding. Scuff the surface with a scuff pad and degrease the surface with **Archemya's WG-201 Wax & Grease Remover**.

## 2. Mix the Basecoat:

Mix at a 1:1 Ratio: 1 Part 1181 Jet Black Factory Pack Basecoat with 1 Part Urethane Grade Reducer.

## 3. Application:

Recommended gun settings are 1.2-1.4 mm tip at 10 PSI with an HVLP gun. Spray 2-3 medium coats of mixture onto the substrate with a 5-10 minute\*\* flash time between coats. Suggested flash time decreases with increase in temperature. You can continue to topcoat after 30 minutes or until it is tack-free.



<sup>\*\*</sup> Dependent on Temperature



<sup>\*\*\*</sup> Results were obtained with 1:1 mix with medium urethane grade reducer